

**CONFOR™ M Foams**

CONFOR M slow-recovery foams, offer a unique combination of physical characteristics, high energy absorption properties and temperature-softening behavior. Soft and flexible, they are suitable for highly diverse applications, from shock isolation in electronics equipment to padding and cushioning in medical devices.

CONFOR M foams exhibit unusually low compression set, highly damped properties and provide excellent energy absorption. They soften on contact with a warm surface—allowing uniform pressure distribution and firm, yet fluid, support. Because the open-celled foams are breathable, non-irritating in dermal contact, they are ideal for medical and body contact cushioning applications.

*Cushioning*—CONFOR M foams can provide flexible protection in a variety of cushioning applications, from body contact padding to electronics packaging.

*Shock absorption*—With their excellent energy absorption characteristics CONFOR M materials offer a range of impact protection and isolation for dynamic loads, while maintaining consistent static load performance.

*Vibration isolation*—CONFOR M foams’ unique combination of slow recovery and high energy absorption allows the materials to offer effective damping and vibration isolation.

TYPICAL PROPERTIES				
PROPERTY	CF-40M	CF-42M	CF-45M	CF-47M
<b>Density Nominal kg/m<sup>3</sup> (lb/ft<sup>3</sup>)</b> ASTM D3574	96 (6.0)	96 (6.0)	96 (6.0)	96 (6.0)
<b>Flammability</b> UL 94	Listed HBF @ 3mm	Listed HBF @ 3mm	Listed HBF @ 3mm	Listed HBF @ 3mm
FMVSS-302	Meets	Meets	Meets	Meets
California Flame 117–2013	Passes	Passes	Passes	Passes
<b>Ball Rebound (%)</b> ASTM D3574	<1.0	<1.0	<1.0	<1.0
<b>Thermal Conductivity—K Value</b> ASTM C177 W/m•K (BTU in/hr ft <sup>2</sup> F)	.040 (0.28)	.040 (0.28)	.040 (0.28)	.040 (0.28)
<b>Compression Set (%)</b> ASTM D3574 22 hr at 22C (72F) Compressed 50%	1.2	1.0	1.0	1.0
<b>Indentation Force Deflection</b> ASTM D3574 Test B1 (modified) 25% Deflection for 12" x 12" x 2" sample: 22C (72F) at 50% Relative Humidity N (lbf)	97 (22)	155 (35)	213 (48)	280 (63)
<b>Tensile Strength kPa (psi)</b> ASTM D3574 51 mm/min (20 in/min)	48 (7.0)	83 (12)	117 (17)	152 (22)
<b>Tear Strength kN/m (lbf/in)</b> ASTM D3574 51 cm/min (20 in/min) at 22C (72F)	0.29 (1.7)	0.47 (2.7)	0.64 (3.7)	0.82 (4.7)
<b>Compression Load Deflection</b> ASTM D3574 Test C *Modified				
10% kPa (psi)	1.4 (0.20)	2.1 (0.31)	3.1 (0.44)	3.9 (0.57)
20% kPa (psi)	1.8 (0.26)	2.8 (0.40)	4.2 (0.61)	5.6 (0.82)
30% kPa (psi)	2.0 (0.29)	3.0 (0.44)	4.5 (0.66)	5.9 (0.86)
40% kPa (psi)	2.3 (0.33)	3.4 (0.50)	5.0 (0.73)	6.5 (0.94)
50% kPa (psi)	2.9 (0.42)	4.1 (0.59)	5.9 (0.86)	7.6 (1.1)
60% kPa (psi)	3.5 (0.51)	5.4 (0.78)	7.7 (1.1)	9.8 (1.4)
70% kPa (psi)	6.0 (0.87)	8.8 (1.3)	12 (1.8)	16 (2.3)
80% kPa (psi)	16 (2.3)	23 (3.3)	32 (4.6)	40 (5.7)
<b>RoHS Compliant</b>	Yes	Yes	Yes	Yes

The data listed in this data sheet are typical or average values based on tests conducted by independent laboratories or by the manufacturer. They are indicative only of the results obtained in such tests and should not be considered as guaranteed maximums or minimums.

Materials must be tested under actual service to determine their suitability for a particular purpose.

*Warranty and Limited Remedy:* Aearo Technologies LLC warrants that each Aearo Technologies LLC product meets the applicable Aearo Technologies LLC product specification at the time Aearo Technologies LLC ships the product. Aearo Technologies LLC MAKES NO OTHER EXPRESS OR IMPLIED WARRANTIES OR CONDITIONS, INCLUDING ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If the Aearo Technologies LLC product does not conform to this warranty, the sole and exclusive remedy is, at Aearo Technologies LLC's option, replacement of the Aearo Technologies LLC product or refund of the purchase price.


*Limitation of Liability:* Except where prohibited by law, Aearo Technologies LLC will not be liable for any loss or damage arising from the Aearo Technologies LLC product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted.





## CONFOR™ M FOAMS

Material Summary Sheet 9



**Offering solutions for a wide range of applications such as...**

- Positioning and support devices
- Sports and medical padding
- Electronic devices

