



## ISOLOSS™ SL MOLDING MATERIALS

Material Summary Sheet 12



**Offering solutions for a wide range of applications such as...**

Lab and office equipment

Computers and peripherals

Telecommunications and electronics

Industrial equipment

Disk drives



### ISOLOSS™ SL Molding Materials

ISOLOSS SL series elastomers are highly damped, low modulus, thermoset compounds with exceptional molding stability. The material exhibits high internal damping, excellent resistance to creep and compression and can be metal-bonded during molding.

- Halogen-free per IEC 61249-2-21
- RoHS Compliant
- Highly damped thermoset product for noise, shock and vibration control

TYPICAL PROPERTIES				
PROPERTY	SL-20300	SL-35300	SL-50300	SL-60300
<b>Description</b>	Synthetic Rubber	Synthetic Rubber	Synthetic Rubber	Synthetic Rubber
<b>Hardness</b> ASTM D2240 Type A Durometer 23C (73F) 5 sec impact 15 sec impact	21 19	31 30	47 45	58 56
<b>Flammability</b> UL 94	Listed HB @ 2.3mm-2.5mm	Meets HB @ 3mm	Listed HB @ 3mm	Meets HB @ 3mm
<b>Compression Load Deflection kPa (psi)</b> ASTM D575 at 0.51 cm/min (0.2 in/min) 10% kPa (psi) 20% kPa (psi) 30% kPa (psi)	117 (17) 221 (32) 352 (51)	193 (28) 379 (55) 607 (88)	338 (49) 669 (97) 1096 (159)	517 (68) 1013 (132) 1689 (222)
<b>Compression Set (%)</b> ASTM D395 Method B 22 hr at 22C (72F) 22 hr at 70C (158F)	3 7	4 6	2 7	3 4
<b>Tensile Strength kPa (psi)</b> ASTM D412	4185 (600)	5667 (822)	10149 (1472)	10721 (1555)
<b>Tear Strength kN/m (lbf/in)</b> ASTM D624	11.4 (65)	20.1 (115)	18.9 (108)	24.15 (138)
<b>Temperature Range C</b> Peak Damping Performance Temperature Range @ 10 Hz @ 100 Hz @ 1000 Hz	-23 to 29 -18 to 47 -14 to 71	-21 to 30 -16 to 47 -12 to 72	-5 to 42 -2 to 63 4 to 82	-10 to 35 -4 to 47 -4 to 47
<b>RoHS Compliant</b>	Yes	Yes	Yes	Yes

*Technical Information: The technical information, recommendations and other statements contained in this document are based upon tests or experience that E-A-R Thermal/Acoustic Systems believes are reliable, but the accuracy or completeness of such information is not guaranteed.*

*Product Use: Many factors beyond E-A-R Thermal/Acoustic Systems's control and uniquely within user's knowledge and control can affect the use and performance of a E-A-R Thermal/Acoustic Systems product in a particular application. Given the variety of factors that can affect the use and performance of a E-A-R Thermal/Acoustic Systems product, user is solely responsible for evaluating the E-A-R Thermal/Acoustic Systems product and determining whether it is fit for a particular purpose and suitable for user's method of application.*

*Warranty, Limited Remedy, and Disclaimer: Unless an additional warranty is specifically stated on the applicable E-A-R Thermal/Acoustic Systems product packaging or product literature, E-A-R Thermal/Acoustic Systems warrants that each E-A-R Thermal/Acoustic Systems product meets the applicable E-A-R Thermal/Acoustic Systems product specification at the time E-A-R Thermal/Acoustic Systems ships the product. E-A-R Thermal/Acoustic Systems MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the E-A-R Thermal/Acoustic Systems product does not conform to this warranty, then the sole and exclusive remedy is, at E-A-R Thermal/Acoustic Systems's option, replacement of the E-A-R Thermal/Acoustic Systems product or refund of the purchase price.*

*Limitation of Liability: Except where prohibited by law, E-A-R Thermal/Acoustic Systems will not be liable for any loss or damage arising from the E-A-R Thermal/Acoustic Systems product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.*

